

FullCure®830 VeroWhite

Property	ASTM	Results (Metric)		Results (Imperial)	
Tensile Strength	D-638-03	MPa	49.8	psi	7,221
Modulus of Elasticity	D-638-04	MPa	2,495	psi	361,775
Elongation at Break	D-638-05	%	20	%	20
Flexural Strength	D-790-03	MPa	74.6	psi	10,817
Flexural Modulus	D-790-04	MPa	2,137	psi	309,865
Izod Notched Impact	D-256-06	J/m	24.1	ft lb/in	0.45
Shore Hardness	Scale D	Scale D	83	Scale D	83
Rockwell Hardness	Scale M	Scale M	81	Scale M	81
HDT at 0.45 MPa	D-648-06	°C	47.6	°F	118
HDT at 1.82MPa	D-648-07	°C	43.6	°F	110
Tg	DMA, E''	°C	58	°F	136
Ash Content	NA	%	<0.4	%	<0.4
Water Absorption	D570-98 24 Hr	%	1.47	%	1.47